



Supplier of Welding Alloys

Nickel Alloy Coated Electrodes

Oxford Alloy® 112

SPECIFICATIONS

AWS 5.11
ASME SFA 5.11

CLASSIFICATIONS

AWS ENiCrMo-3
UNS W86112

DESCRIPTION / APPLICATION

Oxford Alloy 112 is used for shielded-metal-arc welding of Inconel® alloy 625, Incoloy® alloy 825, Inco® alloy 25-6MO, and other molybdenum-containing stainless steels. This electrode is also used for surfacing of steel and for welding various corrosion-resistant alloys such as alloy 20. The weld metal has high strength at room and elevated temperatures and has exceptional corrosion resistance, including resistance to pitting, crevice corrosion, and polyphonic acid stress-corrosion cracking. Oxford Alloy 112 is useful for many dissimilar joints involving Inconel® alloys, Incoloy® alloys, stainless steels, low-alloy steels, and carbon steels. This electrode can be operated in all welding positions. The power supply is direct current, electrode positive.

AWS Chemical Composition						
Ni	C	Mn	Fe	S	Cu	Si
55.0 min	0.10 max	1.0 max	7.0 max	0.02 max	0.50 max	0.75 max
Cr	Cb+Ta	Mo	P	OET		
20.0- 23.0	3.15- 4.15	8.0- 10.0	0.03 max	0.50 max		

TYPICAL MECHANICAL PROPERTIES

Tensile strength: 114,500 psi 790 MPa
Yield strength: 89,500 psi 620 MPa
Elongation: 34%

INCONEL, INCOLOY and MONEL are trademarks of the Special Metal Group of Companies

Please contact our sales department for more information at 800-562-3355 or 225-273-4800.

Data contained in this publication are typical of the products and properties described, but are not suitable for specifications.
OXFORD ALLOYS is a registered trademark of Oxford Alloys, Inc.